

Amendm nts to Claim

1 (original). A laminate structure comprising a layer of fabric, wherein a first polymer having a first stress index is substantially contained within the fabric layer and at least one layer of a second polymer coated onto at least one surface of the fabric, the second polymer having a second stress index higher than the first stress index.

2 (original). The structure of Claim 1, wherein the first polymer has a stress index of about 5 MPa or less and the second polymer has a stress index of least about 6 MPa.

3 (original). The structure of Claim 1, wherein the first polymer has a stress index of about 6 MPa or less and the second polymer has a stress index of least about 7 MPa.

4 (original). The structure of Claim 3 wherein the first polymer is ethylene methyl acrylate.

5 (original). The structure of Claim 2, wherein the first polymer has a stress index of about 4 MPa or less.

6 (original). The structure of Claim 2, wherein the second polymer has a stress index of least about 9 MPa.

7 (original). The structure of Claim 1, wherein the first polymer is selected from the group consisting of ethylene copolymer having a total comonomer content of at least 35 weight percent; thermoplastic elastomers having a Shore A hardness of 90 or less; fully crosslinked rubber polymers having a Shore A hardness of 90 or less; and polyvinyl chloride having a Shore A hardness of 90 or less.

8 (original). The structure of Claim 7, wherein the ethylene copolymer is selected from the group consisting of ethylene n-butyl acrylate carbon monoxide, ethylene vinyl acetate, ethylene vinyl acetate carbon monoxide, ethylene butyl acrylate, ethylene n-butyl acrylate glycidyl methacrylate, ethylene ethyl acrylate, ethylene acrylic acid, ethylene ethyl acrylate glycidyl methacrylate, and ethylene methyl acrylate glycidyl methacrylate.

9 (original). The structure of Claim 7, wherein the thermoplastic elastomer is selected from the group consisting of styrene ethylene butylene styrene and polypropylene/ ethylene propylene diene monomer rubber.

10 (original). The structure of Claim 1, wherein the second polymer is selected from the group consisting of ethylene copolymer; polyethylene; polypropylene; polyvinyl chloride; polypropylene/ethylene propylene diene monomer and styrene ethylene butylene styrene.

11 (original). The structure of Claim 1, having a trapezoidal tear strength of at least about 80% of the trapezoidal tear strength of the fabric.

12 (original). The structure of Claim 1, having a trapezoidal tear strength of at least about 18 kilograms in the machine direction.

13 (original). The structure of Claim 1, wherein the fabric comprises a polyolefin selected from the group consisting of polyethylene and polypropylene.

14 (original). The structure of claim 13, wherein the fabric is a spunbonded polypropylene.

15 (original). The structure of claim 1, wherein the fabric is a nonwoven material.

16 (original). The structure of claim 1, wherein the fabric is a woven material.

17 (currently amended). A laminate structure comprising a layer of fabric, wherein a polymer having a stress index of about 6 MPa or less and a first portion of the polymer is substantially contained within the fabric layer and a second ~~second~~ portion of the polymer is coated onto at least one surface of the fabric.

---